

TECHNICAL DATA SHEET

www.regalfloorpaint.co.uk

Anticorrosive Quickdry Primer

Product Description & Recommended Use

- Single-pack, quick drying, high-build primer.
- Provides good durability and corrosion resistance with moderate to good film build.
- Made with the latest anti-corrosive agents.
- Trouble-free application by spray, roller or brush for small areas.
- Excellent durability in all environments.

Standard Colours	Slate Grey and Red Oxide
Dry Film Appearance	Flat
Spreading Rate	5-8m ² per litre (spray application), dependent on film thickness (10m ² @ 50µm)
Touch Dry @20°C	30 minutes - 1 hour
Recoating Time @20°C	Minimum 12 hours
Typical Wet-Film Thickness	100-150µm per coat
Typical Dry-Film Thickness	50-75µm per coat
Solids by Volume	50% (ASTM D2697) ±3%, dependent on colour
VOC Information	430g per litre (from formula to satisfy EU Solvent Emissions Directive)
Application Temperature	10-35°C
Application Method	Ideally spray; roller or brush for small areas
Substrates	Suitably cleaned and dry surfaces
Thinners	Thinning not recommended. For cleaning, use standard thinners.
Flash Point	>25°C
Pack Size	5 litre can; 20 litre can; 205 litre barrel
Shelf Life	12 months

Key Benefits

- High Performance
- Quick Dry
- Formulated with High Quality Synthetic Resins & Anticorrosive Technology

Complies with all current legislation at the time of writing. See MSDSXXX for safety information